



US006271278B1

(12) **United States Patent**
Park et al.

(10) Patent No.: **US 6,271,278 B1**
(45) Date of Patent: *Aug. 7, 2001

(54) **HYDROGEL COMPOSITES AND SUPERPOROUS HYDROGEL COMPOSITES HAVING FAST SWELLING, HIGH MECHANICAL STRENGTH, AND SUPERABSORBENT PROPERTIES**

(75) Inventors: **Kinam Park, West Lafayette, IN (US); Jun Chen, Hatfield, PA (US); Haesun Park, West Lafayette, IN (US)**

(73) Assignee: **Purdue Research Foundation, West Lafayette, IN (US)**

(*) Notice: This patent issued on a continued prosecution application filed under 37 CFR 1.53(d), and is subject to the twenty year patent term provisions of 35 U.S.C. 154(a)(2).

Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

(21) Appl. No.: **08/855,499**

(22) Filed: **May 13, 1997**

(51) Int. Cl.⁷ **C08F 36/04**

(52) U.S. Cl. **521/150; 521/102; 521/109.1; 521/121; 521/125; 521/128; 521/130; 521/140; 521/142; 521/146; 521/149; 521/182; 521/183; 521/186; 521/187**

(58) Field of Search **521/102, 109.1, 521/121, 125, 128, 130, 140, 142, 146, 149, 150, 182, 183, 186, 187**

(56) **References Cited**

U.S. PATENT DOCUMENTS

3,551,556	12/1970	Kliment et al. .
3,641,237	2/1972	Gould et al. .
3,826,678	7/1974	Hoffman et al. .
4,178,361	12/1979	Cohen et al. .
4,525,527	6/1985	Takeda et al. .
4,529,739	7/1985	Scott et al. .
4,649,164	3/1987	Scott et al. .
4,801,457	1/1989	Heller et al. .
5,002,814	3/1991	Knack et al. .
5,089,606	2/1992	Cole et al. .
5,147,343	9/1992	Kellenberger .
5,149,335	9/1992	Kellenberger et al. .
5,154,713	10/1992	Lind .
5,292,777	3/1994	DesMarais et al. .
5,324,561	6/1994	Rezai et al. .
5,338,766	8/1994	Phan et al. .
5,352,448	10/1994	Bowerstock et al. .
5,403,870	4/1995	Gross .
5,424,265 *	6/1995	Weinstein 502/400
5,451,613	9/1995	Smith et al. .
5,462,972 *	10/1995	Smith et al. 521/64
5,624,967 *	4/1997	Hitomi et al. 521/64
5,750,585	5/1998	Park et al. .

FOREIGN PATENT DOCUMENTS

WO 97/27
884 A1 8/1997 (WO) .

OTHER PUBLICATIONS

K. Park, "Enzyme-digestible swelling hydrogels as platforms for long-term oral drug delivery: synthesis and characterization", *Biomaterials* (Sep. 1988), pp. 435-441, vol. 9, Butterworth & Co.

C.J. Benning, *Plastic Foams: the physics and chemistry of product performance and process technology*, vol. 1, *Polymer Engineering & Technology*, (1969) Chptrs. 6, 7, 9, 10, 14. Wiley-Interscience.

F. Rodriguez, *Principles of Polymer Systems*. 2nd ed. (1982) pp. 363-378, Hemisphere Publ. Corp.

Plastic Foams, Part II. K. Frisch and J. Saunders, ed. (1973) Chptrs. 12, 15, 17. Marcel Dekker, Inc.

F.A. Shutov, *Integral/Structural Polymer Foams: Technology, Properties and Applications*. (1986) Chptrs. 1, 21. Springer Verlag.

"Absorbent PVA Material Finds Medical Applications," *Medical Product Mfg. News Hotline* (Apr. 1, 1995).

Vichterle et al., Hydrophilic gels for biological use, *Nature*, 185: 117-118, 1960.

Shalaby et al., In vitro and in vivo studies of enzyme-digestible hydrogels for oral drug delivery, *J. Controlled. Rel.*, 19: 131-144, 1992A.

Shalaby et al., Use of ultrasound imaging and fluoroscopic imaging to study gastric retention of enzyme-digestible hydrogels, *Biomaterials*, 13:289-296, 1992B.

Chirila et al., Poly (2-hydroxyethyl methacrylate) sponges as implant materials: In vivo and in vitro evaluation of cellular invasion, *Biomaterials*, 14: 26-38, 1993.

Skelly et al., Novel macroporous hydrogel adsorbents for artificial liver support haemoperfusion systems, *Polymer*, 20: 1051-1052, 1979.

Oxley et al., Macroporous hydrogels for biomedical applications: Methodology and morphology, *Biomaterials*, 14: 26-38, 1993.

Barvic et al., Biologic properties and possible uses of polymer-like sponges, *J. Biomed. Mater. Res.*, 1: 313-323, 1967.

(List continued on next page.)

Primary Examiner—John M. Cooney, Jr.

(74) Attorney, Agent, or Firm—James H. Meadows

(57) **ABSTRACT**

A superporous hydrogel composite is formed by polymerizing one or more ethylenically-unsaturated monomers, and a multiolefinic crosslinking agent, in the presence of particles of a disintegrant and a blowing agent. The disintegrant, which rapidly absorbs water, serves to greatly increase the mechanical strength of the superporous hydrogel and significantly shorten the time required to absorb water and swell. Superporous hydrogel composites prepared by this method have an average pore size in the range of 10 μm to 3,000 μm . Preferred particles of disintegrant include natural and synthetic charged polymers, such as crosslinked sodium carboxymethylcellulose, crosslinked sodium starch glycolate, and crosslinked polyvinylpyrrolidone. The blowing agent is preferably a compound that releases gas bubbles upon acidification, such as NaHCO₃. Improved hydrogel composites formed without a blowing agent are also provided.